

CLAIMS:

- Sub A
1. A lacquer composition, obtainable by a method comprising the steps of mixing together an organosilane compound and silica particles under basic conditions, characterized in that a metal alkoxide is added to the reaction mixture.
 - 5 2. A lacquer composition according according to claim 1, characterized in that the metal alkoxide is a zirconium alkoxide, an aluminum alkoxide, a titanium alkoxide or a mixture thereof.
 - 10 3. A lacquer composition according to claim 1 or 2, characterized in that the metal alkoxide comprises a metal diketonate.
 - 15 4. A lacquer composition according to claim 1, characterized in that the organosilane compound is an epoxysilane.
 5. A lacquer composition according to claim 4, characterized in that the epoxysilane is 3-glycidyloxypropyltrimethoxysilane.
 - 20 6. A lacquer composition according to claim 1, characterized in that at least a second organosilane compound is present.
 7. A lacquer composition according to claim 6, characterized in that the second organosilane compound comprises a tetra-alkoxysilane.
 - 25 8. A method of applying a lacquer coating to a substrate in which method a lacquer composition is applied to the substrate and cured, thereby forming the lacquer coating, characterized in that a lacquer composition as claimed in claims 1-7 is used.
 9. Product provided with a lacquer coating, characterized in that the lacquer coating is obtained by using the method as claimed in claim 8.

10. A starting material composition for obtaining a lacquer composition as claimed in any of the claims 1-7, comprising an organosilane compound, silica particles, a base, and a metal alkoxide.

add A 2

2005.10.10 12:46:03